

1 Article

2 **Investigating Fly Ash as a Sustainable SCM for Self-Compacting Concrete: Workability and Strength Analysis**3
4 Hanzla Khan ^{1,*}, Abdul Wahid ^{1,*}, Muhammad Fahad Awais ¹, Sultan Muhammad Junaid ¹, Shakeel Ahmed ¹, Ibrahim ¹6 ¹ Department of Civil Engineering, University of Engineering and Technology, Taxila, 47080, Pakistan.7 * Correspondence: (khanhanzla264@gmail.com)(H.K) and (jwahid087@gmail.com) (A.W)9 **Abstract**

10 Self-compacting concrete (SCC) is modern concrete which can flow and compact naturally
11 without requiring mechanical vibration. This attribute minimizes the labour and time
12 spent on construction thus SCC is highly efficient. The use of supplementary cementitious
13 materials or SCMs has gained momentum over the recent years to partially substitute ce-
14 ment in conventional concrete to maintain strength without increasing cost and environ-
15 mental degradation. Nevertheless, the use of SCMs in self-compacting concrete is scarcely
16 being researched, and thus individuals are not eager to apply it due to the uncertainty in
17 its performance. The present work studies the behaviour of SCC on the addition of fly ash
18 instead of some cement to bridge this gap. Cement was substituted with fly ash in weight
19 percentages of 0%, 5%, 10%, 15%, 20%, and 25%. Standard concrete cubes were made for
20 every mix ratio. To assess the fresh SCC's workability and identify the ideal fly ash con-
21 tent, the slump flow test was performed. A Compressive Testing Machine (CTM) was
22 used to evaluate the samples' compressive strength following 14 days and 28-days water
23 curing period. The results showed that the maximum workability was achieved when fly
24 ash was substituted for 15% of the cement. Furthermore, blends with 10% to 15% fly ash
25 replacement had the highest compressive strength. These results show that fly ash, when
26 used in the right amounts, improves flowability and strength in SCC and is a cost-effective
27 partial substitute for cement.

28 **Keywords:** Self-Compacting Concrete; fly ash; compressive strength; workability; slump
29 flow; sustainable construction.

30

31 **1. Introduction**

32 With the new development of the modern construction especially reinforced con-
33 crete, Self-Compacting Concrete (SCC) was invented to replace the traditional compaction
34 process [1,2].As Self-Compacting Concrete (SCC) it is able to flow under its weight, fill
35 form works completely and harden without vibration [3].This significantly lowers the la-
36 bour expenses, noise as well as the construction time when compared to the conventional
37 compaction process and also it is in a position to give superior finishes as well as strength
38 to the surface [4].

39 To improve sustainability and performance characteristics of SCC, Supplementary
40 Cementitious Materials (SCM) like Fly Ash, Silica Fume, and Ground Granulated Blast
41 Furnace Slag (GGBS) are often added as admixtures [5]. Fly ash, an ash obtained from
42 burning coal, can be greatly appreciated for its pozzolanic reaction and spherical particles,

43 thus making it more workable and with lesser hydration heat [6]. Although SCM admix-
44 tures have shown some advantageous effects, SCC mix sensitivity demands optimal ad-
45 justment for balancing workability and strength properties [7]. The main intention of ex-
46 ploring and presenting research on SCC and SCM admixtures would be to identify and
47 assess its mechanical properties and workability with varying proportions of Fly Ash as
48 substitute materials for cement. Specifically, it would be apt to identify and ascertain an
49 optimal percentage replacement based on maximum compressive strength and retention
50 of SCC property with added advantage due to the presence of Sika ViscoCrete-3110 su-
51 perplasticizer admixture [8].

52 2. Literature Review

53 The self-compacting concrete (SCC) became the solution of the issues related with
54 intermittent compaction and honeycomb processes in dense reinforced zones. SCC will
55 allow a concrete mix that can flow under its own gravity and filling formwork to the full
56 extent without any compaction or vibration [1]. SCC will, as a rule, experience superior
57 surface finish, passing capacity, and labour and equipment requirements than traditional
58 concrete [2]. SCC study was first focused on optimal proportions of cement, water, fines
59 and coarse aggregates and high range water reducing admixtures with the aim of coming
60 up with feasible mixtures with high flow and resistance against segregation [3]. It has been
61 demonstrated that rheological properties and stability are very sensitive functions consid-
62 ering binder, aggregate, and admixture proportions. Recent research findings have em-
63 phasized the need to incorporate supplementary cementitious materials such as fly ash,
64 silica fume, and slag as admixtures with an alternative percentage of cement materials so
65 as to make SCC more eco-efficient [4]. The introduction of admixtures does not only min-
66 imize the clinker and consequent CO₂ emission but also enhances the durability and the
67 mechanical strength with an optimum mix. Special attention has been paid to fly ash due
68 to its pozzolanic nature, fine nature and sphericity, which attributes to its ability to in-
69 crease the workability and water requirement of concrete mixes [5]. According to the lit-
70 erature review on the fly ash concrete materials, it is indicated that the optimum replace-
71 ment proportions can optimize the pore structure, minimize the permeability, and max-
72 imize the late-stage strength, though too much replacement can have an impact on the
73 early-stage strength. Under the SCC mixing system, it has been reported that several stud-
74 ies have demonstrated the enhancement of fly ash significantly in terms of its flowability
75 and stability due to its filler and ball-bearing attributes due to its smooth particles [6]. It
76 reacts pozzolanic reaction with calcium hydroxide at an intermediate replacement ratio
77 to make calcium silicate hydrate. As noted by Khatib, SCC blends with fly ash could have
78 the same or superior mechanical properties than conventional SCC when proper propor-
79 tional replacement ratios were used [7]. Also, the analytical comment on eco-efficient SCC
80 reports that fly ash blends with industrial waste materials could be just as effective and
81 with significantly lowered environmental footprints of concrete production [8]. High-
82 range water-reducing admixtures that contain polycarboxylate ether-based superplasti-
83 cizers are required to produce SCC with low water to binder proportions and high flow
84 without segregation. According to the product information presented on the Sika Vis-
85 coCrete-3110 admixtures, the admixtures are supposed to provide high workability reten-
86 tion, high slump flow, with the possibility of compatibility with binary binders that use
87 SCMs such as fly ash [9]. One can conclude based on the available literature that fly ash is
88 a potentially viable SCM of SCC and it can be used to enhance workability and long-term
89 strength and the sustainable construction activity, by appropriately controlling the per-
90 centage and mix parameter variables [10].
91
92

3. Materials and Methods

3.1. Materials

The materials selected for this study included OPC was used as the main binder. Fly ash was used as cement replacement. Particles of fly ash are mostly spherical, which serves as a lubricant to enhance flowability and enables pozzolanic reactions in the hardened concrete. Coarse aggregates used were of a nominal size range 12–18 mm; natural sand was selected as a fine aggregate to fill up voids and provide support for self-compaction. Admixtures: Superplasticizer Sika ViscoCrete-3110 is a polycarboxylate ether-based superplasticizer. It reduces water demand, improves the flowability without segregation. Other SCMs: GGBS and lime powder were added into the binder system to improve cohesiveness and durability, and to enhance eco-efficiency of the mix.

3.2. Mix Design and Sample Preparation

Mix design percentage of fly ash was also tested as varied and other parameters were maintained constant. Thus, 6 combinations of mixes have been made with the replacement of fly ash by cement in 0% (control), 5, 10 and 15, 20 and 25 percent by weight as shown in Figure 1. In the compressive strength test, 36 cubic specimens (6 in x 6 in x 6 in) were cast. Mix Proportions Specific mix proportions per cubic meter: The cement content varied depending on the degree of fly ash replacement level, whereas GGBS and lime powder were held constant to allow homogeneity within the mix. The selection of grading and proportions of coarse and fine aggregates have been made to comply with both self-compacting concrete requirements and sufficient flowability and stability of fresh mixes.



Figure 1. Concrete cube moulds sample preparation.

3.3. Testing Procedures

Workability Test: Slump flow test was done as soon as the fresh self-compacting concrete was mixed to assess the flowability and uniformity of the fresh self-compacting concrete. The test was conducted with regards to suitable ASTM test procedures as far as slump flow of SCC is concerned. Due to the mix, the diameter of the spread concrete was measured in two perpendicular directions, and the overall mean was calculated as the slump flow.

Compressive Strength Test: The cubic specimens were cured in 14 and 28 days, and in water. A Compression Testing Machine (CTM) of 2000 KN was utilized in the process of conducting a destructive compression test, and the ultimate load at failure was registered to determine the compressive strength of each mix, as shown in Figure 2.



Figure 2. Sample under testing.

4. Results

4.1. Workability Analysis

The mix workability for SCC mixtures was determined using the slump flow test. It clearly indicated that addition of fly ash generally enhances the flow properties of concrete. Table 1 explain the slump flow values for different fly ash percentages

Table 1. Slump Flow values for different Fly Ash percentages.

Fly Ash Percentage (%)	Slump Flow (mm)
0	70
5	670
10	678
15	722
20	711
25	701

As Table demonstrates, the control mix (0% fly ash) has very low flow (70 mm), and this is not enough to have self-compacting concrete. The inclusion of fly ash (5 percent) by massively raising the slump flow to 670 mm shows that the fly ash ability was enhanced significantly. The optimum working point was 15% replacement, where the slump flow was 722 mm and thereafter the values of slump flow slightly decreased but still fell within the normal range of acceptable values of SCC as stipulated in the standard guidelines as shown in Figure 3.




Figure 3. Effect of fly ash percentage on slump flow of SCC.

4.2. Compressive Strength

The compressive strength was measured on the days of 14 and 28 days to determine the impact of fly ash content on the mechanical performances of the hardened concrete. Table 2 presents the values for both durations.

Table 2. Cube compressive strength, 14 and 28 days old.

Fly Ash (%)	14-Day Compressive Load (KN)	28-Day Compressive Load (KN)
0	260	285
5	271	282
10	304	325
15	319	337
20	254	274
25	221	264

The compressive load capacity rose with fly ash content and attained its highest limit of 337 KN at a fly ash content of 28 days and this is greater than the compressive load capacity with the control mixes 285 KN. The 10% and 15% fly ash mixes thus showed high performance in terms of load bearing than the control. At 20% and 25% replacement, however, the load values at 28 days dropped to 274 KN and 264 KN, respectively, which was drop in strength at higher fly ash, as also illustrated in Figure 4.




Figure 4. Effect of fly ash percentage on 14-day and 28-day compressive load of SCC cubes.

5. Discussion

The findings also reveal that a 15 percent substitution of cement with fly ash offers a good compromise between the workability and compressive strength in self-compacting concrete mixes. This replacement level is comparable with ranges that have been identified in prior research in which moderate content of fly ash improved fresh and hardened characteristics of SCC. The fine grading of fly ash particles and the spherical shape of the particles provide a ball bearing effect that decreases the internal friction between the solid particles and increases the flowability of the fresh mix. The mechanism contributes to the sudden rise in slump flow with the introduction of fly ash (0% to 5% replacement) and the highest slump flow attained at 15% replacement in the current study.

The rise of strength up to 15 percent fly ash substitution can be explained by the pozzolanic reactions, where in the hydration of cement, the fly ash reacts with the calcium

hydroxide that releases additional calcium silicate hydrate (C₃S) thus compacting the microstructure. Also, the fine fly ash particles create a filler effect, meaning that they fill the openings between cement grains and aggregates, resulting in a smaller and more uniform matrix with increased load-bearing capacity. Replacement: Compressive strength is reduced at 20 percent fly ash replacement and 25 percent fly ash replacement, which is in line with the dilution effect that is described in the literature under high contents of SCM. During these increased replacement values, the reduced cement content can yield less primary hydration product, and the surplus fine particles can modify the water requirement and packing of the system and this may interfere with the microstructure and lead to low strength.

6. Conclusion

This paper examined the workability and strength characteristics of self-compacting concrete (SCC) with different percentages of fly ash used as a partial substitute of cement. Conclusions, which are based on the outcomes of the experiment, are as follows: Workability: Fly ash considerably increases the flow qualities of SCC. The highest replacement of 15% recorded the highest slump flow of 722 mm, which shows that it was the most workable mix. Compressive Strength: The ideal percentage of replacement in compressive strength is 15 percent, which the concrete had the best load-bearing capacity at 14 and 28 days in comparison with the control mix and other levels of fly ash. Sustainability: It is a feasible approach to replace 15 percent of cement by fly ash and form more economical and eco-friendly concrete because the use of fly ash will decrease the use of cement, but the mechanical and workability characteristics should be satisfactory. Limitations: The replacement levels above 15 percent will result in appreciable decrease in compressive strength and thus fly ash contents above 15 percent should be employed with care especially in structural components that need higher strength levels.

Author Contributions: H.K. and A.W.; Conceptualization, methodology, software, validation, formal analysis, investigation, S.A.; resources, S.M.J.; data curation, writing—original draft preparation, I.; writing—review and editing, M.F.A.; visualization. All authors have read and agreed to the published version of the manuscript

Funding: This research received no external funding

Institutional Review Board Statement: Not applicable

Informed Consent Statement: Not applicable

Data Availability Statement: Data available in the article

Conflicts of Interest: The authors declare no conflicts of interest

References

1. Rawat, V.S.; Khan, M.Z. Self-Compacting Concrete. *Int. J. Creat. Res. Thoughts* 2022, 1–5.
2. Alterary, S.S.; Marei, N.H. Fly ash properties, characterization, and applications: A review. *J. King Saud Univ. Sci.* 2021.
3. Jennings, H., & Thomas, J. J. (2009). *Materials of cement science primer*. Northwestern University Infrastructure Technology Institute.
4. Wang, J.; Zhou, J.; Kangwa, J. *Self-compacting concrete adopting recycled aggregates*; Woodhead Publishing, 2023.
5. Souza, A.M.; Carvalho, J.M.F.; Santos, C.F.R.; Ferreira, F.A.; Pedroti, L.G.; Peixoto, R.A.F. On the strategies to improve the eco-efficiency of self-compacting concrete using industrial waste: An analytical review. *Constr. Build. Mater.* 2022.
6. Sika. Sika ViscoCrete-3110 Product Data Sheet. Available online: <https://pak.sika.com/> (accessed on 14 June 2025).
7. Nayak, D.K.; Abhilash, P.P.; Singh, R.; Kumar, R.; Kumar, V. Fly ash for sustainable construction: A review of fly ash concrete and its beneficial use case studies. *Clean. Mater.* 2022.
8. EFNARC. *The European Guidelines for Self-Compacting Concrete*; EFNARC: Farnham, UK, 2005.
9. Khatib, J.M. Performance of self-compacting concrete containing fly ash. *Constr. Build. Mater.* 2008.

217
218

10. Brouwers, H.J.H.; Radix, H.J. Self-Compacting Concrete: Theoretical and experimental study. *Cem. Concr. Res.* 2005, 35, 2116–2136.